# **CHEMTRONICS<sup>®</sup> Technical Data Sheet**

# **TDS # CW2610**

# **CircuitWorks<sup>®</sup> Rubber Keypad Repair Kit**

#### **PRODUCT DESCRIPTION**

CircuitWorks<sup>®</sup> Rubber Keypad Repair Kit permanently repairs rubber keypads by restoring conductivity to worn, intermittent, and nonconductive carbon contacts. This product easily returns rubber keypads to like-new condition. This system is flexible and very durable. The CircuitWorks<sup>®</sup> Rubber Keypad Repair Kit provides a silver/carbon coating that is effective and long lasting.

- Repairs nonconductive keypads
- Excellent electrical conductivity
- Wear-resistant coating
- Excellent adhesion
- System has 72 hour pot life at room temperature and relative humidity <65%</li>
- Testing shows repairs can withstand over 500,000 simulated keystrokes

## **TYPICAL APPLICATIONS**

CircuitWorks<sup>®</sup> Rubber Keypad Repair Kit is excellent for rework and repair applications including:

- Telephones
- Controllers
- Carbon Contact Keyboards
- Communication Equipment
- Miscellaneous Keypads

### TYPICAL PRODUCT DATA AND PHYSICAL PROPERTIES

#### Composition

Material	Part A	Silver/Carbon/Rubber
	Part B	Hardener
Color	Part A	Dark Gray/Silver
	Part B	Amber Clear
Specific Gravity	Part A	2.5 - 2.7
	Part B	1.0
Cured Compound		
Tack-Free Time @ 25°C (75°F)		(75°F) 1 Hour
Return to Service Time		24 Hours
Complete Cure @ 25°C(75°F)		5°F) 72 Hours
Electrical Conductivity		Excellent
Durability		Excellent
Flexibility		Excellent
Shelflife		18 months

#### COMPATIBILITY

CircuitWorks<sup>®</sup> Rubber Keypad Repair Kit has excellent compatibility with most materials. As with any adhesive/sealant, compatibility with substrate should be determined on a non-critical area prior to use.

#### **USAGE INSTRUCTIONS Read MSDS carefully prior to use.**

**Mixing:** Pour the liquid in Part B into the container of Part A. Stir thoroughly for two minutes.

**Application:** Paint the worn carbon contacts with the mixed conductive material using the enclosed applicator brushes.

**Curing:** At room temperature ( $<25^{\circ}$ C), material dries tack-free in one hour. Repaired keypads can be returned to service in 24 hours. Ultimate properties are achieved in 72 hours. For faster drying, expose the material to approximately 190°F (90°C) for 10 minutes. DO NOT EXCEED 212°F (100°C).

#### TECHNICAL & APPLICATION ASSISTANCE

Chemtronics<sup>®</sup> provides a technical hotline to answer your technical and application related questions. The toll free number is: **1-800-TECH-401.** 

### AVAILABILITY

CW2605 1 set containing: 3g / 0.36 oz. Adhesive 0.33g / 0.01 oz. Curing Agent

#### NOTE:

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. CHEMTRONICS<sup>®</sup> does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

## MANUFACTURED BY: ITW CHEMTRONICS<sup>®</sup> 8125 COBB CENTER DRIVE KENNESAW, GA 30152 1-770-424-4888 REV.

REV. E (09/02)

