

TECHNICAL DATA SHEET

Compound Code

E13001701

Compound Reference

EMKA EPDM ES-06

Compound Description – EPDM 0.6 Sponge, Sulphur Cured

Properties	Test Method	E13001701	Unit
Physical Properties:			
Specific Gravity (Raw Material)	DIN 53 479	1.10	kg/l
(Average in Finished Product)		0.65	g/cm ³
Tensile Strength	DIN 53 504	9.30	N/mm ²
Elongation at Break	DIN 53 504	353	%
Compression Set	22 hrs @ 70C 22 hrs @ 100C		10-15% 20-25%
Low Temperature Brittleness	ISO 812	Pass	Pass

Remarks: All results obtained on press plates cured 10'/180°C
